

VITAL TECHNICAL SDN. BHD.

Technical Data Sheet

VT-164 / VT-164SE / VT-166 / VT-177 Vital Clear RTV



Issuance date: 31/03/08 Revision date: 12/05/21 Revision No.: 21-01

VT-164 / VT-164SE / VT-166 / VT-177 Vital Clear RTV

PHYSICAL STATE

Paste

ODOR

Vinegar-like

COLOR

Translucent

CURING TIME(t=5mm)

2 days

PACKAGING

85 g/tube carded (144 packs/carton)
70 g/tube carded (144 packs/carton)
32 g/tube carded (144 packs/carton)
15 g x 10/tube carded (48 packs/carton)

SHELF LIFE

24 months

STORAGE

Store in a dry and cool place with temperature below 30 °C

APPLICATION TEMPERATURE

-20 °C - 50 °C

SERVICE TEMPERATURE Up to 150 °C



DESCRIPTION

Vital Clear RTV is An original gasket maker formulated for heavy duty applications. It forms reliable "formed-in-place" gaskets that resist cracking, shrinking and migration caused by thermal cycling. Ideal to replace almost any cut gasket and can be used to coat pre-cut gaskets to increase reliability. It is permanently flexible and stable at temperature of between -80 °F to 600 °F (-62 °C to 315 °C) intermittent. It is also highly resistant to automotive fluids.

TECHNICAL

DATA

Curing system : Acetoxy
Specific gravity : 1.02
Tensile at break : ≥1.2 MPa
Elongation at break : >300 %
Shore A hardness : ≥18

FEATURES

- Temperature resistant up to 600 °F (315 °C)
- Make leak-proof gaskets in seconds
- Remain flexible and durable

APPLICATION

 Gasketing of machinery casing like compressors, pumps & gear box. Sealing of flange pipe joints, access door etc.

APPLICATION DIRECTION

- 1. Surfaces must be clean, dry and free of dirt, grease, oil or water.
- 2. Puncture the tube with cap and install nozzle. Apply 2 4 mm bead to one surface only.
- 3. Fix the parts to be assembled before the tack-free time.
- 4. Uncured sealant can be cleaned up with mineral spirits.
- 5. Replace cap after use and store in a cool, dry place.

CAUTION

Product releases acetic acid during application and curing. Keep out of reach of children. Use in well ventilated areas. Safety data sheet available on request. For further health and safety information, consult the latest safety data sheet.

LEGAL NOTES

Every endeavour has been made to ensure that the information given herein is true and reliable but it is given only for the guidance of our customers. The company cannot accept any responsibility for the loss or damage that may result from the use of the information, due to the possibility of variations of processing or working conditions and of workmanship outside our control. Users are advised to confirm suitability of this product by their own tests.