



VITAL TECHNICAL SDN. BHD.

Technical Data Sheet

VT-150  
Vital Blue RTV



Issuance date: 05/03/2024

Revision date: 05/03/2024

Revision No.: 24-01

# VT-150 Vital Blue RTV

## PHYSICAL STATE

Paste

## ODOR

Vinegar-like

## COLOR

Blue

## TACK-FREE TIME

≤25 minutes

## PACKAGING

85 g/tube carded  
(144 packs/carton)

## SHELF LIFE

24 months

## STORAGE

Store in a dry and cool place with temperature below 30 °C

## APPLICATION TEMPERATURE

-20 °C – 50 °C

## DESCRIPTION



An original gasket maker formulated for heavy duty applications. It forms reliable "formed-in-place" gaskets that resist cracking, shrinking and migration caused by thermal cycling. Ideal to replace almost any cut gasket and can be used to coat pre-cut gaskets to increase reliability. It is permanently flexible and stable at temperatures between -80 °F to 500 °F (-62 °C to 260 °C) intermittent. It is also highly resistant to automotive fluids.

<b>TECHNICAL DATA</b>	Curing system	: Acetoxy
	Specific gravity	: 1.02
	Tensile at break	: ≥1.2 MPa
	Elongation at break	: >300 %
	Shore A hardness	: ≥18

<b>FEATURES</b>	<ul style="list-style-type: none"><li>Temperature resistant up to 500 °F (260 °C)</li><li>Low volatile formula</li><li>Safe for all models</li><li>Pressure resistant</li><li>Forms leak-proof gaskets in seconds</li><li>Remains flexible and durable</li></ul>
-----------------	------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------

<b>APPLICATION</b>	<ul style="list-style-type: none"><li>Rear main bearing cap split line, damper keyway sealing, differential cover, intake end seals, OHC cap, oil pan corner seals, oil pan gasket, side cover plate, thermostat housing, timing cover, transmission pan, valve cover gasket, vibration damper, water pump cover gasket and intake manifolds.</li></ul>
--------------------	---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------

<b>APPLICATION DIRECTION</b>	<ol style="list-style-type: none"><li>Surfaces must be clean, dry and free of dirt, grease, oil or water.</li><li>Puncture the tube with cap and install nozzle. Apply 2 – 4 mm bead to one surface only.</li><li>Fix the parts to be assembled before the tack-free time.</li><li>Uncured sealant can be cleaned up with mineral spirits.</li><li>Replace cap after use and store in a cool, dry place.</li></ol>
------------------------------	--------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------

<b>Hazard and Precautionary Statements</b>	Product releases acetic acid during application and curing. Keep out of reach of children. Use in well ventilated areas. Safety data sheet available on request. For further health and safety information, consult the latest safety data sheet.
--------------------------------------------	---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------

<b>LEGAL NOTES</b>	Every endeavour has been made to ensure that the information given herein is true and reliable but it is given only for the guidance of our customers. The company cannot accept any responsibility for the loss or damage that may result from the use of the information, due to the possibility of variations of processing or working conditions and of workmanship outside our control. Users are advised to confirm suitability of this product by their own tests.
--------------------	---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------