

	VITAL TECHNICAL SDN. BHD.	 
	Technical Data Sheet	
	VT-630 MS Flooring Adhesive	

Issuance date: 27/12/11

Revision date: 30/05/2023

Revision No.: 23-01

VT-630 MS Flooring Adhesive

One-component Elastic Wood Flooring Adhesive



PHYSICAL STATE

Soft Paste

STANDARD COLOR

(B21) Light brown

TACK-FREE TIME

20 – 40 minutes

WORKING TIME

~ 30 minutes
(at 25 °C & 50% R.H.)

PACKAGING

- 600 mL/sausage
(20 sausages/carton)
- 24 kg/pail
(3x8kg packs per pail)
(24kg ≈ 15.3 Liter)
- 15 kg/carton
(2x7.5kg packs per pail)

SHELF LIFE

12 months

STORAGE

Store in a dry and cool place with temperature below 30 °C

APPLICATION TEMPERATURE

15 °C to 35 °C

SERVICE TEMPERATURE

-20 °C to 90 °C

DESCRIPTION



An eco-friendly wood flooring adhesive formulated with advanced MS Polymer technology, eliminating common problems associated with traditional polyurethane adhesives. It cures on exposure to atmospheric moisture, and quickly forms a tenacious but elastic bond on wood flooring and wall decorative materials. When cured, it is waterproof and is not adversely affected by exposure to moisture or water. Its elastic characteristic allows the wood floor to expand and contract without adhesion failures.

The adhesive can be troweled easily. Its non-slump formula enables notched trowel ridges hold firm, bridging gaps between wood flooring and sub floor and reducing floor hollowness problem. Since it does not contain water or solvent, it will not cause dimensional changes in wood. It is also safe because it does not contain hazardous materials like isocyanate, and has a very low VOC content.

TECHNICAL DATA

Base	: One-component MS (Modified Silane) Polymer	
Curing system	: Moisture curing	
Specific gravity	: 1.58 – 1.62 g/mL	
Ultimate tensile strength	: 1.6 N/mm ²	ASTM D412
Elongation at break	: 180 %	ASTM D412
Shore A hardness	: 40	ASTM C661
Low VOC compliance	: Yes	SCAQMD Rule 1168
VOC content	: 9.49 g/L	USEPA Test method 24

FEATURES

- Certified Green Sealant Adhesive
- Single-component – Ready for use, no mixing required
- Resistant to aging - Permanently elastomeric
- Free of water, 100% solid content - No dimensional changes in wood
- Free of solvent - Non-etching & no shrinkage
- Free of isocyanate - Non-hazardous
- Low odor & low VOC - meets LEED/SCAQMD rule 1168
- Notched trowel ridges hold firm - Minimize hollow spots by bridging gaps
- Rapid strength build-up and short curing time - Fast job completion
- Easy surface clean up - Easy cleaning on prefinished wood
- Non-flammable, non-hazardous, stable shelf life – Easy storage

APPLICABLE TESTS / STANDARDS

- VT-630 meets the requirements of:
- Leadership in Energy and Environmental Design (LEED) v4.1 EQ compliant
 - Low VOC - USEPA Method 24 under SCAQMD Rule 1168

APPLICATION

Ideal for bonding wood floors to concrete, concrete screeds, cement / sand screeds, anhydrite screeds, plywood, cured leveling compounds, epoxy membrane, OSB (underlayment grade), particle board, gypsum board, ceramic tiles, stone, terrazzo, radiant heated subfloors, metal decking, steel, aluminum, etc.

TYPES OF FLOORING

- Most types of wood flooring including but not limited to:
- Solid Wood Plank/Strip
 - Parquet
 - Wood Blocks
 - Wood Mosaic
 - Engineered Wood
 - Laminated Plank
 - Bamboo
 - Acrylic Impregnated Wood
 - Plywood
 - Others

(Scan to learn how to use)



Visit product page:
<https://vitaltechnical.com/product/vt-630-ms-flooring-adhesive/>



VITAL TECHNICAL SDN. BHD.

Technical Data Sheet

VT-630 MS Flooring Adhesive



Issuance date: 27/12/11

Revision date: 30/05/2023

Revision No.: 23-01

VT-630

MS Flooring Adhesive

- PREPARATION**
- Subfloor must be solid and structurally sound, flat, smooth, clean, permanently dry, no indentations and anti-adherents, as well as resistant to pressure.
 - Subfloor must be free of dust, dirt, grease, wax, loose paint, oil, sealers of ANY type, curing compounds, bond breakers, asphaltic residue, liquid adhesive remover, strippers, chemicals, or any other foreign substances that can potentially affect bonding. Cleaning the subfloor with an industrial vacuum cleaner is recommended.
 - Subfloor must be flat to 3mm over 3 meter, otherwise it will increase the risk of hollow spots under timber overlay.
 - Any existing coating or adhesives must be completely removed. Mechanical treatment (e.g. shot blasting, grinding or sanding) may be required to achieve subfloor conditions mentioned above.
 - It is recommended to verify that the moisture content of the slab is <5.5%, and moisture vapour transmission rate is <15g/m² per 24 hour before commencing installation works. Excessive moisture in subfloor could affect wood flooring.
 - To prevent moisture migration and subsequent wood swelling or cupping, ground floor slabs or new concrete slabs that do not meet the moisture conditions above are recommended to be coated with **V-tech VT-507 FloorSeal Epoxy Moisture Barrier**.
 - Before installation, check moisture content of wood is as recommended by wood flooring manufacturer (generally 9% ±2%).
 - Radiant heated subfloors should be turned off 24 hours prior to and during installation to prevent premature curing of the adhesive.
 - Recommended air temperature during installation – between 10°C - 35°C (50°F - 95°F), Relative Humidity – between 40% and 75%, subject to the requirements specified by wood flooring manufacturer.
 - Do not install if the walls and ceilings of the area are not dry (e.g. after plastering or painting etc.)

APPLICATION DIRECTION

Sausage sachet:

1. Place the sausage sachet in a suitable application gun and snip off the end. Cut the tip off the nozzle to suit the application.
2. Apply the adhesive with appropriate force and speed.
3. Make sure the wood is positioned on subfloor within the working time of the adhesive.

Packs in Pail:

1. Remove the lid and cut open the foil liner. Once open, the entire contents should be used within a short period of time.
2. Spread the adhesive with the proper notched trowel, apply uniformly on the subfloor. Avoid adhesive pools and excessive adhesive thickness by passing the trowel evenly through the adhesive at a 45 degree angle.
3. Place wood in the adhesive within working time, correctly position it and press down firmly or tamp down with a rubber hammer to ensure good overall contact. Wood may slip and move at first so be sure to secure the initial row to limit movement and hold patterns.
4. Minimum 80% of adhesive contact coverage is recommended to achieve proper installation of parquet floor. Place heavy objects to hold the wood firmly in place during the curing time, especially on bowed boards or boards over low spots. It may be necessary to sort out bowed planks before installation.
5. When installing near a solid object or wall, leave ample room for expansion. Installing wood too tight against a stationary object will not allow room for normal wood expansion, which may cause a failure.
6. When the installation is complete, use wedges or some object to hold wood in place while adhesive dries. Remove wedges after initial setting of adhesive (approximately 2 hours) to allow for normal expansion of wood. Failure to remove wedges can cause the wood flooring to buckle and pop off the substrate.
7. Restrict foot traffic for a minimum of **12-16 hours**. Wait a minimum of **24 hours** before sanding and varnishing.

Note: Follow wood flooring manufacturer's guidelines for layout, design and any special precautions for installation.

CLEAN UP

- Can be cleaned up with acetone or mineral spirits when wet.
- Cured materials can only be removed mechanically.



VITAL TECHNICAL SDN. BHD.

Technical Data Sheet

**VT-630
MS Flooring Adhesive**








Issuance date: 27/12/11

Revision date: 30/05/2023

Revision No.: 23-01

VT-630
MS Flooring
Adhesive

COVERAGE

Floor Type	Trowel	Coverage
<ul style="list-style-type: none"> finger block parquet 	 <p>Square Notch 3 mm x 3 mm x 3 mm</p>	Up to 2.0 m ² /L
<ul style="list-style-type: none"> ≤13mm solid wood ≤13mm engineered wood 	 <p>V Notch 4 mm x 3 mm</p>	Up to 1.4 m ² /L
	 <p>V Notch 5 mm x 4 mm</p>	Up to 1.2 m ² /L
<ul style="list-style-type: none"> 9-13 mm solid wood >13 mm engineered wood <19 mm parquet 	 <p>Square Notch 6 mm x 6 mm x 3 mm</p>	Up to 1.0 m ² /L
<ul style="list-style-type: none"> >13 mm solid wood 4' x 4' plywood 	 <p>Square Notch 6 mm x 6 mm x 6 mm</p>	Up to 0.9 m ² /L
<ul style="list-style-type: none"> Trowel type and size are selected based on flooring type. Coverage rates shown are only guidelines. Coverage will vary with trowel size/type, angle the trowel is held to the subfloor, and the absorption level of substrate. Generally, use a fine trowel for wood of smaller sizes and/or smooth substrates, and a coarse trowel for wood of larger sizes and/or rough substrates. 		

LIMITATIONS

- Below grade applications are subject to wood flooring manufacturer's recommendations.
- Do not use on wet, dusty, contaminated or friable substrates.
- Do not dilute the adhesive.
- Do not install solid wood over cutback residue or over VCT/vinyl.
- Resistant to water, dilute acids, and diluted caustic solutions, temporarily resistant to fuel, animal fats and oils, not resistant to organic acids, concentrated caustic solutions.
- Will not prevent damage to wood flooring induced by excessive moisture transmission due to environmental factors like leaky pipe.

CAUTION

Keep out of reach of children. Contains aminosilane. May produce an allergic reaction. Safety data sheet available on request. For further health and safety information, consult the latest safety data sheet.

LEGAL NOTES

Every endeavour has been made to ensure that the information given herein is true and reliable but it is given only for the guidance of our customers. The company cannot accept any responsibility for the loss or damage that may result from the use of the information, due to the possibility of variations of processing or working conditions and of workmanship outside our control. Users are advised to confirm suitability of this product by their own tests.