


	VITAL TECHNICAL SDN. BHD.	  
	Technical Data Sheet	
	VT-131 Auto Sealer	

Issuance date: 31/03/08

Revision date: 09/04/21

Revision No.: 21-01

Product Specifications:

Curing system	: Oxime
Appearance	: Paste
Colour	: Black
Odour	: Slight unique odour
Specific gravity:	: 1.02
Tack-free time (JIS A 1439)	: ≤30 min
Tensile at break	: ≥0.8 MPa
Elongation at break	: ≥250%
Application temperature	: -20 °C to 50 °C
Service temperature	: -50°C to 150 °C
Shelf life	: 24 months
Features	: Permanently flexible
	: Durable
	: Indoor and outdoor use

Packaging

Product Code	Content	Inner Box	Carton
VT-131	75 g tube card	12	144



Product Description:

A one-component, general purpose, black colour silicone sealant formulated for indoor and outdoor applications. It can be applied to horizontal or vertical surfaces. It will form a waterproof seal which resists oil, water, weather, vibration and grease. It does not dry out or become brittle.

Applications:

It seals, bonds, repairs, mends and secures glass, metal, plastics, fabric, weather-stripping and vinyl tops. It also be used to protect and repair electrical wiring, windshields, door frames, seams and roofs.

Directions:

1. Surfaces must be clean, dry and free of dirt, grease, oil or water. Puncture tube with cap.
2. Apply product to substrate.
3. If used as adhesive: Press firmly and let it cure for six hours before moving it.
4. If used as sealant: Tool within five minutes of extrusion.
5. Replace cap after use and store in a cool, dry place.
6. Product can be cleaned with mineral spirit.

Caution:

Product releases methylethylketoxime during application and curing. May cause an allergic skin reaction. Wear protective gloves / protective clothing / eye protection / face protection/hearing protection. If skin irritation or rash occurs: Get medical attention. Take off contaminated clothing and wash it before reuse.

Storage:

- Store in a dry and cool place with temperature below 30 °C.
- Use within 24 months from date of production.

Every endeavour has been made to ensure that the information given herein is true and reliable but it is given only for the guidance of our customers. The company will not accept any responsibility for the loss or damage that may result from the use of the information, due to the possibility of variations of processing or working conditions and of workmanship outside our control. Users are advised to confirm suitability of this product by their own tests.