




VITAL TECHNICAL SDN. BHD.

Technical Data Sheet

VT-760 Wood and Parquet Adhesive



Issuance date: 12/11/2014

Revision date: 29/06/2021

Revision No.: 21-03

VT-760 Wood and Parquet Adhesive

Water-based Wood Flooring Adhesive

PHYSICAL STATE

Viscous liquid

WET TACK

Aggressive

FLAMMABILITY

Non flammable

COLOUR

White

PACKAGING

500 g/bottle
(24 bottle/ carton)
1 kg/bottle
(12 bottle/ carton)
4 kg/pail
(6 pail /carton)

SHELF LIFE

12 months

STORAGE

Store in a dry and cool place with temperature below 30 °C

DESCRIPTION



VT-760 Wood and parquet adhesive is a water based, non-toxic, and non-corrosive adhesive that is excellent for wood bonding application. It features quick setting, superior bonding strength and it bonds variety of porous substrates.

TECHNICAL DATA

Specific gravity	: 1.18	
Solid content	: 39 %	
Viscosity	: 48,000 cPs	Brookfield LV4, 5rpm
Lap shear strength	: 6.6 N/mm ²	

FEATURES

- Ready to use
- Easy to spread
- Non-toxic
- Water-based
- High bond strength
- Fast curing
- Forms thin gapless layer when set
- Solvent-free and low odour

APPLICATION

- Ideal for parquet flooring, wood joining, furniture repair, parquet installation or repair, wooden frames.

APPLICATION DIRECTION

Substrate Preparation

1. Substrates must be dry, absorbent, level, sound, free of dust, loose particles, paint, wax, oil, rust, and traces of gypsum.
2. The moisture content of the screed must be lower than the maximum prescribed by the timber manufacturer.
3. Check moisture throughout the entire thickness of substrates, using carbide hygrometer.
4. Floating screeds over insulation or light weight layers (e.g. light weight concrete) and slabs on grade must be provided with a moisture barrier to prevent rising damp.
5. To repair cracks in the substrate, consolidate screeds and level uneven screeds.

Adhesive Applications

1. Stir the adhesive before using. Remove the skin surface if any.
2. Apply the adhesive to the substrate with notched trowel suitable to the format.
3. The open time is 30 minutes under normal temperature (10 °C to 40 °C) and humidity conditions, which must be taken into consideration when applying the adhesive.
4. If skin forms on the adhesive before parquet installation, the adhesive must be removed and replaced.

Parquet Installation

1. The parquet to be installed must be stored in a dry, sheltered area not subject to the vapour condensation and must be insulated from the ground.
2. Check the moisture content of the timber and the ambient humidity before installation.
3. Press the wood parquet firmly onto the wet adhesive to ensure good contact.
4. Leave a gap of approximately 10 mm width around the perimeter, columns, and any elements crossing the floor.
5. Do not bond edges of wood strips together. (follow the parquet manufacturer's recommendations for installation)

**VITAL TECHNICAL SDN. BHD.****Technical Data Sheet****VT-760
Wood and Parquet Adhesive**

Issuance date: 12/11/2014

Revision date: 29/06/2021

Revision No.: 21-03

VT-760**Wood and Parquet
Adhesive**

CURING TIME ▪ Floors are set to light traffic after 48 hours. For parquet polishing, wait for at least 10 days to ensure that the wood has reached the proper stability and that the adhesive is completely dry.

CONSUMPTION ▪ Depending on the type of substrates and notched trowel selection, the adhesive consumption range from 0.6 kg to 1.0 kg / m². For laminated plank, the recommended adhesive coverage is at least 80 %. For solid wood, minimum 95 % adhesive coverage is required.

LIMITATIONS Not recommended for following applications:

- Use in very cold areas. In cold weather, rooms must be heated.
- Use on anhydrite or magnesium screed.
- Use on screeds where there may be possible rising damp (must insert a moisture barrier between ground and the screed).
- Use if the screed is not dry and has a moisture content higher than recommended by the wood manufacturer (check moisture content throughout the entire thickness)

CAUTION Keep out of reach of children. Safety data sheet available on request. For further health and safety information, consult the latest safety data sheet.

LEGAL NOTES Every endeavour has been made to ensure that the information given herein is true and reliable but it is given only for the guidance of our customers. The company cannot accept any responsibility for the loss or damage that may result from the use of the information, due to the possibility of variations of processing or working conditions and of workmanship outside our control. Users are advised to confirm suitability of this product by their own tests.